

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) Publication number:

**0 252 463**  
**A2**

(12)

# EUROPEAN PATENT APPLICATION

(21) Application number: **87109662.4**(22) Date of filing: **04.07.87**

(51) Int. Cl.<sup>4</sup>: **C08F 220/10**, **C08F 2/44**,  
**A01N 25/10**, **A61K 9/22**,  
**A61K 47/00**, **A23L 1/22**,  
**A23L 1/236**, **A23L 1/275**

(30) Priority: **07.07.86 US 882609**  
**20.05.87 US 53609**

(43) Date of publication of application:  
**13.01.88 Bulletin 88/02**

(84) Designated Contracting States:  
**BE CH DE FR GB IT LI NL**

(71) Applicant: **DOW CORNING CORPORATION**

**Midland Michigan 48640(US)**

(72) Inventor: **Abrutyn, Eric S.**  
**9 Westminster Drive**  
**Middletown NY 10940(US)**  
Inventor: **Chromeczek, Richard C.**  
**RFD 1**  
**Litchfield Conn. 06759(US)**  
Inventor: **Scarfo, Louis J.**  
**18 Lyons Place**  
**New Britain Conn. 06052(US)**

(74) Representative: **Patentanwälte RUFF, BEIER**  
**und SCHÖNDORF**  
**Neckarstrasse 50**  
**D-7000 Stuttgart 1(DE)**

(54) **Lattice-entrapped composition.**

(57) This invention relates to solid compositions wherein a non-cosmetic functional material is entrapped in the lattice of the cross-linked polymer during in situ polymerization of the monomers forming the polymer lattice. The invention provides for conversion of solid and/or liquid products into solid, free-flowing forms by entrapment of the functional materials in a hydrophobic polymer lattice.

**EP 0 252 463 A2**

## BACKGROUND AND SUMMARY OF THE INVENTION

5 This invention relates to solid compositions wherein a functional group is entrapped in the lattice of a cross-linked hydrophobic polymer during in situ polymerization of the monomers forming the polymer lattice. More particularly, the invention relates to comb-like polymers which have entrapped various chemicals and provide for their sustained release.

The art is replete with attempts to render functional materials amenable to release on demand through encapsulation. Encapsulation confines materials in discrete units or capsules as the result of coating particles of the material with an encapsulant. The coating wall or encapsulating material used in encapsulation includes natural or synthetic polymers which permit release of the functional material by fracture, degradation or diffusion.

10 Handbook of U.S. Colorants for Food, Drugs and Cosmetics by Daniel M. Marmion, A. Wile. Inter-science Publication, Second Edition, 1984, which is herewith incorporated by reference, discloses food flavorants and pigments which could be utilized in the present invention.

15 In Pesticides: Preparation and Mode of Action by R. Cremllyn, John Wiley and Sons Publication, 1978, and Pesticides Guide: Registration, Classification and Applications by J. Keller and Associates, Inc., Neenah Wisconsin, Section 167.3, 1984 which are herein incorporated by reference, disclose the various pesticides, and insect attractants which may be utilized in connection with the invention.

20 It is an object of the present invention to provide a novel form of entrapment of the functional material which does not encapsulate the functional material.

This invention provides a unique combination of polymers and functional material, which results in compositions wherein the functional materials rather than being encapsulated by coating materials are dispensed throughout and entrapped within a polymeric lattice. These compositions are useful for incorporating a variety of functional materials into a variety of products such as cosmetic and non-cosmetic products. Furthermore, the amount of functional materials which can be entrapped in the lattice are much higher than heretofore achievable by encapsulation.

### 30 Brief Description of the Drawings

A better understanding of the present invention will become more apparent from the following detailed description of the invention taken in conjunction with the formal drawings, wherein:

35 Figures 1A - 1D are photomicrographs at increasing powers of magnification of an emollient ester entrapped in a polymer lattice.

Figures 2A - 2D show the visual effect at various degrees of magnification of a lattice-entrapped functional material product when it is applied in a thin layer.

Figures 3A - 3D are photomicrographs of lattice-entrapped functional material products wherein the functional material is a fragrance which is homogeneously miscible with the polymer.

40 Figures 4A - 4C are photomicrographs of a lattice-entrapped emollient; a lattice wherein the emollient has been extracted, and a polymer which is formed without functional material in the polymer lattice.

### Description of the Invention

45 This invention relates to a solid, lattice-entrapped composition which comprises from about 5% to about 95% by weight of a cross-linked polymer lattice and from about 95% to about 5% by weight of a functional material. Unlike known methods of entrapping the functional material by encapsulating the functional material, the present invention entraps the functional material directly within the hydrophobic polymer lattice during in situ polymerization of the monomers.

It has now been discovered that a wide variety of materials which are either liquids or solids can be converted to free-flowing powders or beads by entrapment of the materials in a polymeric lattice. The entrapped materials are not themselves encapsulated in any way, i.e. enclosed by capsules, coatings or sacs; rather, they are dispersed throughout and entrapped within the polymeric lattice. Such lattice-entrapped products have properties that are superior to the encapsulated products of the prior art. The

polymeric lattice functions to hold and protect the entrapped material without encapsulating it, probably through solution or swelling, and the lattice is capable of making the material available by a variety of mechanisms including pressure, diffusion and extraction. Significantly, when the lattice-entrapped materials of this invention are incorporated into cosmetic, non-cosmetic and toiletry products the polymeric lattice itself contributes beneficial effects to the overall product structure. According to the structure and chemical properties of the system heterogeneous or homogeneous entrapment can be achieved. If the entrapped chemical is a thermodynamically good solvent (swelling agent) for the system, a homogeneous (gel) entrapment will result. In the opposite case of a thermodynamically bad solvent, separation of phases during the polymerization will occur and a heterogeneous (macromolecular) entrapment will result.

Homogeneous or heterogeneous entrapment is naturally also dependent on the structure and amount of the crosslinker, where higher crosslinking density results in a heterogeneous product.

While this invention also shows the in situ lattice entrapment of emollient-moisturizers within the polymeric lattice, those skilled in the art will recognize that a wide variety of other functional materials can be entrapped within the polymeric lattice either alone or in combination with the emollients or moisturizers. The invention contemplates that a wide variety of water insoluble organic liquids and solids may be incorporated within the lattice. In fact, any functional material which will not chemically react with the polymer system comprising the polymeric lattice can be entrapped within the polymeric lattice.

The solid lattice-entrapped, i.e., nonencapsulated, compositions of this invention are prepared by combining in one step a functional crosslinking monomer, a monofunctional monomer and the functional material to be entrapped within the lattice under such conditions as to thereafter initiate polymerization. As used herein, the term "functional crosslinking monomer" is meant to include di- or polyfunctional monomers having two or more polymerizable double bonds, while the term "monofunctional monomer" is meant to include a polymerizable monomer having one double bond. Functional crosslinking monomers useful in the invention may be a polyunsaturated monomer selected from the group consisting of a mono- or di-ester of an alcohol and an alpha-beta unsaturated carboxylic acid; polyunsaturated polyvinyl ether of a polyhydroxy alcohol; mono- or poly unsaturated amides and cycloaliphatic esters of alpha-beta unsaturated carboxylic acids. Examples of such functional cross-linking monomers include polyethylene glycols having a molecular weight up to about 5000 dimethacrylate, triethylene glycol dimethacrylate, tetraethylene glycol dimethacrylate and trimethylol propane ethoxylated triacrylate, available under the trademark CHEM-LINK®176, ditrimethylol propane dimethacrylate; propylene, dipropylene and higher propylene glycols having a molecular weight up to about 5000 including polyethylene glycol dimethacrylate, 1,3 butylene glycol dimethacrylate, 1,4 butanediol dimethacrylate, 1,6 hexanediol dimethacrylate, neopentyl glycol dimethacrylate, pentaerythritol dimethacrylate, bisphenol A dimethacrylate, divinyl (trivinyl) benzene, divinyl (trivinyl) toluene, triallyl maleate, triallyl phosphate, diallyl itaconate, and allyl methacrylate.

The monofunctional monomer of the novel polymeric system of this invention includes hydrophobic and hydrophilic monounsaturated monomers. The monomers include alkyl methacrylates and acrylates having straight or branched chain alkyl groups with 1 to 30 carbon atoms, preferably 5 to 18 carbon atoms. Preferred monofunctional monomers include lauryl methacrylate, 2-ethylhexyl methacrylate, isodecylmethacrylate, stearyl methacrylate, hydroxy ethyl methacrylate, hydroxy propyl methacrylate, diacetone acrylamide, phenoxy ethyl methacrylate, tetrahydrofurfuryl methacrylate and methoxy ethyl methacrylate.

The structure of the cross-linked polymer is characterized by layered ordering of the side chains.

The side chains separated by the backbone chains are packed in parallel layers. The backbone chains of the macromolecules are spaced by distances roughly equal to the length of the side chain.

In addition to other factors, the structure of the linkage of the side chain to the main backbone chain may vary the degree of conformational freedom at the side chain junctions. While poly alpha olefins do not have conformational freedom of the side chain segments around the C-C bond, polyacrylates and polyvinyl ethers have greater degree of freedom due to the C-O bond. The freedom of rotation of the poly methacrylates is limited by the steric hindrance of the methyl group in the backbone chain.

The functional materials to be lattice-entrapped within the novel polymeric lattice of this invention are selected from materials which are normally either liquids or solids. Functional materials such as pigments, perfumes, pheromones, synthetic insect attractants, pesticides including juvenile hormone analogs, herbicides, pharmaceuticals, anti-microbial agents, sunscreens, light stabilizers, fragrances, flavors including sweeteners and the like, may be entrapped within the novel polymeric lattice of this invention.

The crosslinking monomer, monofunctional monomer and functional material are combined in a ratio such that the resultant novel lattice-entrapped composition of this invention comprises from about 5% to about 95% by weight of a cross-linked polymer lattice and from about 95% to about 5% by weight of the entrapped functional material. The ratio of crosslinking monomer to monofunctional monomer in the cross-

linked polymer lattice can vary within the range of 99:1 to 1:99. While not restricting the invention to any precise composition, in a typical product of this invention, the crosslinking monomer, monofunctional monomer and functional material are combined in a ratio such that the resultant novel cross-linked polymer lattice comprises from about 60 to about 80% by weight of the functional material entrapped therein.

5 The cross-linked polymer lattice containing the entrapped functional material results from the in situ polymerization of the monomer mixture which already has the functional material to be entrapped therein. Generally, this results simply from mixing the crosslinking monomer and the monofunctional monomer, dissolving the functional material in the combined monomers to form a uniform mixture, and thereafter inducing polymerization. Polymerization may be induced by conventional initiators such as peroxides and  
10 the like, or by irradiation or redox systems. Polymerization usually occurs at temperatures between about 0 to 120°C., preferably about 80°C. The time and temperature of polymerization may be varied in accordance with the nature of the functional material, its concentration, and the attributes of the desired entrapped system, but in all instances, the polymerization occurs only after the monomers and the functional material are combined.

15 The physical properties of the lattice-entrapped functional materials may be influenced by several factors such as the precise combination of crosslinking monomer and monofunctional monomer selected, the ratio in which these two components are combined with one another and with the functional material. Accordingly, the lattice-entrapped materials of this invention which exist in the form of discrete, free-flowing powders or beads may be hard and have the ability to withstand rather substantial shearing, or the powders  
20 or beads may be soft, in which form they disintegrate or spread to form a uniform layer with minimal pressure. In general, the greater the ratio of cross-linked polymer lattice to the functional material, the harder the lattice-entrapped material. The lattice-entrapped functional material ranges in particle size from about 0.001 millimeters to about 3 millimeters.

A simple test has been developed to predict with reasonable accuracy whether or not a particular  
25 combination of crosslinking monomer, monofunctional monomer and functional material will polymerize to form the lattice-entrapped functional material of this invention. According to this test, approximately equal quantities of crosslinking monomer, monofunctional monomer and functional material are combined in a test tube and polymerized. If the resultant polymerized product is turbid or cloudy, a heterogeneous macroporous structure has formed which is a positive indication that the components tested can be combined in a  
30 ratio such that subsequent polymerization will result in the products of this invention. There are exceptions to this rule, in that certain combinations of materials may result in the production of a clear polymer. If, however, when the clear polymer is extracted from the reaction mixture it is determined to be cloudy or turbid, indicating a heterogeneous, macroporous structure, a positive test has again occurred. After a positive test, i.e., an initial turbid or cloudy appearance on polymerization of the test tube size sample,  
35 further tests are conducted by varying the ratio of monomers to functional material to determine those ranges in which discrete particles, and not clumps or masses, are obtained on polymerization. With the foregoing test in mind, and recognizing the need to obtain discrete particles and not clumped or massed polymers, it will be appreciated that those skilled in the art can select appropriate cross-linking monomer, monofunctional monomers and the ratio in which these materials are to be combined to obtain the lattice-  
40 entrapped materials of this invention.

The novel lattice-entrapped functional materials of this invention are versatile products having application in many and varied types of products. As stated previously, liquid and solid functional products form  
lattice-entrapped products which are suitable for incorporation in a wide variety of healthcare products, pesticidal agents, insect attractants, anti-microbial agents, pharmaceuticals, pesticides, disinfectants, sun  
45 screens, light stabilizers, flavors, pigments and perfumes may also be used as functional materials in the lattice-entrapped materials of this invention.

A primary advantage of formation of the novel lattice-entrapped functional materials of this invention is the conversion of liquid or solid functional materials into powdery, free-flowing materials through incorporation in a syneresis-free polymeric lattice. The lattice entrapment of the functional material provides the  
50 ability to hold the functional materials for controlled application on demand. Other advantages of the lattice-entrapping the functional materials of this invention include the ability to convert the solid and liquid functional materials into free-flowing discrete particles ranging in size from fine powders to rather large beads. Still another advantage of this invention lies in the fact that the polymer lattice itself contributes desirable attributes (discussed hereinafter) when the functional materials are trapped therein.

55 The lattice-entrapped functional materials of this invention are easy to handle, convenient to store, and are prepared by relatively non-complex procedures. Lattice-entrapment of the function materials within the cross-linked polymer lattice protects the functional materials from the environment, excessive volatilization, and from ultraviolet light. The lattice-entrapped functional materials are releasable from their entrapped state

within the microscopic lattice by the application of pressure, by extraction and diffuse from the entrapped state due to temperature and humidity changes. Also, it has been found that the desirable characteristics of the lattice-entrapped functional materials, i.e. emollients and moisturizers, are enhanced by the polymer lattice itself. The polymer lattice provides a continuous film-like appearance when applied to a surface, so that the ultimate effect of the lattice-encapsulation of this invention is to extend the effect of the lattice-entrapped materials.

A decided advantage to be obtained by entrapping the functional materials according to this invention results from being able to incorporate substantially greater amounts of functional material in a desired product than is possible through incorporation of the raw functional material without lattice entrapment. For example, it is known that an emollient such as 2-ethyl hexyl oxystearate (WICKENOL® 171) provides improved moisturizing and skin softening qualities to toilet soap, but it is not possible to incorporate more than about 2-5% of such an emollient in conventional toilet soap formulations without seriously detracting from the foaming characteristics of the soap. If, however, the emollient is first formulated in the lattice-entrapped microscopic polymeric lattice of this invention, substantially higher concentrations of the emollient, up to as much as 20% by weight thereof, may be incorporated into the toilet soap formulation, thereby serving to enhance the softening and moisturizing properties of the soap without any deleterious effect on the foaming and esthetic properties of the soap. The polymer portion of the lattice also improves the mechanical properties of the soap.

Another important application for the novel lattice-entrapped functional materials of this invention is in the area of molded wax and/or oil base sticks of the type typically used for antiperspirants, deodorants, lipsticks, sun screens, topical pharmaceuticals, insect repellents, colognes, etc. Typically, these stick-type products must balance many ingredients in order to obtain the desired appearance and function, but the optimal solid wax-oil base stick seems to elude formulators because of problems such as shrinkage, variable rate of deposition, tackiness, and the like, which continue to plague such products. The lattice-entrapped functional materials of this invention offer significant advantages to such stick-type products since they make it possible to substantially reduce the bodying agents (such as natural, vegetable or insect waxes) typically present in such stick products. These advantages result from the fact that the polymeric lattice which entraps the functional material enhances rigidity and strength of the stick while it permits the lattice-entrapped functional materials to produce their desired effect as they are made available from their lattice-entrapped state.

The lattice-entrapped functional materials of this invention are free flowing powders which are easy to handle and convenient to store. The lattice-entrapped functional materials are made available or released when applied either directly or as a component of a product. It is thought that when the entrapped functional material is applied to a surface in a cosmetic or toiletry product it is released as the result of rubbing and spreading in the form of a continuous uniform film protected within a hydrophobic envelope.

A scanning electron microscope (SEM) study was undertaken to better understand how the functional materials are entrapped in the polymer lattice. An objective of the study was to determine how miscible and immiscible functional materials differ in the manner in which they are incorporated into the polymer lattice. Additionally, the investigation showed a comparison of the lattice-entrapped product before and after a simulated application.

Figures 1A - 1D are photomicrographs of 2-ethyl hexyl oxystearate/polymer powder (POLYTRAP®171) entrapped in a polymer powder. The photomicrographs were taken at X20 (Figure 1A), X360 (Figure 1B), X940 (Figure 1C), and X3000 (Figure 1D) power. The photographs indicate that the ester is heterogeneously adsorbed on the surface of a very fine polymer micro-dispersion (cluster) of less than two microns in diameter. In the higher power magnifications, it can be seen that rather than being encapsulated by the polymer, the functional material is entrapped within the polymer lattice.

Figures 2A - 2D show examples of a lattice-entrapped functional material product when the product is applied and spread out, such as when it is applied directly to a surface. In this series of photographs, the material is again POLYTRAP® 171. Figure 2A is an untouched photograph of the lattice-entrapped product. Figure 2B (at X1000) shows the lattice-entrapped film material product after it has been lightly spread. Figure 2C (at X1000) shows the lattice-entrapped film material product after it has been completely spread and further shows that a continuous film material results. Figure 2D (at X15,000) shows a more magnified view of the same product material as Figure 2C. It can be seen from Figure 2D that the film consists of small (less than 2 microns) particles.

Figures 3A - 3D are photomicrographs of the lattice-entrapped functional material product which show the incorporation of a fragrance as the lattice-entrapped functional material. Herein, the fragrance is in the form of POLYTRAP Fragrance Polymer Beads. The various photographs are taken at increasing powers of magnification, X540 (Figure 3A), X2000 (Figure 3B), X3000 (Figure 3C), and X10,000 (Figure 3D). The

fragrance is homogeneously miscible with the polymer, and is therefore very evenly dispersed within the polymer lattice. This can be readily seen by comparing Figure 3C taken at X3,000 with the Figure 1D which is a picture taken at the same magnification, but with the immiscible functional material in the polymer lattice. When the fragrance is homogeneously miscible with the polymer, it can be seen that an almost featureless smooth surface is created.

Figure 4A shows a lattice-entrapped functional material product according to the present invention (POLYTRAP® 171) at a power of X3,000. The same product is shown in Figure 4B; however, the lattice-entrapped emollient has been extracted therefrom. Figure 4C is a product formed without a functional material (POLYTRAP® 235) and consists simply of the blank polymer beads. Figures 4B and 4C are very similar.

These various scanning electron microscopy studies of the lattice-entrappment system of the invention show the effect of an entrapped species on the physical characteristics of the polymer formation. Moreover, the photographs indicate that the functional material is entrapped within the polymer lattice rather than being encapsulated by the polymer. When the functional material is miscible (e.g. fragrance) in the polymer, a homogeneous polymer lattice is formed which produces mechanically tough spheres or beads which can be milled without disturbing the integrity of the structure. When the material is a non-solvent for the polymer, a heterogeneous internal structure is formed.

The cluster of beads formed by either the miscible or immiscible functional material is fragile and when mechanical stress is applied thereto, the clusters will fracture and produce a continuous film of particle size less than two microns, even in the range approaching 0.1 - 0.2 microns.

While it will be appreciated by those skilled in the art that there are many variations in procedure and components, this invention may be illustrated by the following examples:

#### EXAMPLE 1

7 grams of 2 ethylhexyl oxystearate (WICKENOL® 171) was mixed with 1.5 grams of ethylene glycol dimethacrylate and 1.5 grams of lauryl methacrylate in a glass test tube. The solution was deaerated for five (5) minutes and 0.1 ml of t-butyl peroctoate was added and mixed while heating to 80°C in an oil bath. After 20 minutes, the contents solidified; and the mixture was maintained at about 80°C for an additional hour to assure full polymerization. A semi-soft, heterogeneous white opaque polymer mass resulted containing the entrapped ester.

The following examples demonstrate initial screening of the crosslinking monomer, monofunctional monomer and functional material to determine whether or not the combination thereof will form the novel lattice-entrapped products of the invention. In each test the components were combined in a test tube and polymerization initiated and completed. Formation of an opaque polymer mass in the test tube scale test indicated that the components could be combined in large scale polymerization to form the entrapped functional materials of this invention.

#### EXAMPLE 2

Following the procedure of Example 1, the crosslinking monomers tetraethylene glycol dimethacrylate, trimethylol-propane trimethacrylate, trimethylol-propane ethoxy triacrylate, and allyl methacrylate were polymerized in the presence of 70% by weight 2-ethylhexyl oxystearate and 15% by weight lauryl methacrylate. In each case a semi-soft, white opaque polymer mass resulted, indicating suitability for formation of the lattice-entrapped product of this invention. Such a polymer lattice is suitable for entrapment of pharmaceutical preparations for external use, for example, wheat germ glycerides for dermatological therapy or a sunscreen preparation with -paminobenzoic acid or its derivatives.

#### EXAMPLE 3

Following the procedure of Example 1, test tube polymerization was completed varying the types of monomer constituents and their ratios, and the quantity and type of functional material to be entrapped. In each instance, t-butyl peroctoate was used to initiate polymerization at a constant level of 3% by weight, based on the weight of the combined content of monomers and functional material. The components, quantity and test tube results are set forth in Table 1. The following abbreviations are used in Table 1:

TEGDM Ethylene glycol dimethacrylate  
TMPTM Trimethyl propane trimethacrylate  
EGDM Ethylene glycol dimethacrylate  
TPETM Trimethylol propane ethoxylate trimethacrylate  
5 LMA Lauryl methacrylate  
IMA Isodecyl methacrylate  
HMA Hydroxyethyl methacrylate  
DAA Diacetone acrylamide  
PMA Phenoxyethyl methacrylate  
10 MEMA Methoxy ethyl methacrylate

In the aforementioned tests it is possible to use as the functional material any of the wide variety of water insoluble liquids or solid insecticides, pesticides, sunscreens, light stabilizers, pigments, food flavorants, pheromones, synthetic attractants, pharmaceuticals, and the like, either alone or in a suitable non-aqueous solvent, for example, ethanol, mineral spirits, propylene glycol, and the like.

15 Suitable synthetic attractants for pest control products includes 1,1-dimethyl-4(and 5)-chloro-2-methylcyclohexane-1-carboxylate (trimedlure), medlure, siglure, butyl sorbate, cue-lure, methyl eugenol, and the like.

20

25

30

35

40

45

50

55

TABLE I

Test No.	Cross-linking Monomer	Weight %	Mono Functional Monomer	Weight %	Material Entrapped	Weight %	Appearance in Test Tube
1	TEGDH	67.5	LMA	22.5	2 Ethylhexyl sebacate (WICKENOL® 171)	10	Hard-powdery, white opaque polymer mass
2	TMPTM	45	IMA	45	Arachidyl propionate (WAXENOL® 801)	10	Semi-hard, off-white opaque
3	TMPTM	12	IMA	3	Arachidyl propionate (WAXENOL® 801)	85	Semi-soft, off-white opaque
4	EGDM	16.7	SMA	6.3	Di(Ethylhexyl) adipate (WAXENOL® 158)	75	Semi-soft, white opaque
5	EGDM	30	HMA	10.3	Isopropyl Myristate (WICKENOL® 101)	60	Semi-soft, white opaque
6	EGDM	30	LMA	10	Ethanol	60	Hard-powdery, white opaque
7	TEGDH	67.5	SMA	22.5	Stearyl alcohol	10	Very hard, white opaque



Test no.	Cross- linking Monomer	Weight %	Mono Functional Monomer	Weight %	Material Entrapped	Weight %	Appearance in Test Tube
8	TECDM	15	SHA	5	Stearyl alcohol	80	Hard-powdery white opaque
9	EGDM	67.5	DAA	22.5	Propylene glycol	10	Very hard, off- white opaque
10	EGDM	15	DAA	5	Propylene glycol	80	Semi-soft, off- white opaque
11	EGDM	60	LMA	30	Propionic acid	10	Very hard, white opaque
12	EGDM	15	LMA	5	Propionic acid	80	Semi-hard, white opaque
13	TECDM	45	SHA	45	Stearic acid	10	Very hard, white opaque
14	TECDM	10	SHA	10	Stearic acid	80	Semi-hard white opaque
15	EGDM	67.5	SHA	22.5	Polyoxy propyl- ene (30 moles)	10	Very hard, white opaque
16	EGDM	15	SHA	5	cetyl alcohol (WICKENOL 707)	80	Semi-soft, white opaque

5  
10  
15  
20  
25  
30  
35  
40  
45  
50  
55

Test No.	Cross-linking Monomer	Weight %	Mono Functional Monomer	Weight %	Material Entrapped	Weight %	Appearance in Test Tube
17	EGDM	60	DAA	30	Polyoxy propylene (30 moles lanolin)	10	Very hard, white opaque
18	EGDM	15	DAA	5	(WICKEMOL 727)	80	Semi-soft, yellowish, opaque
19	TEGDM	67.5	LMA	22.5	Carbowax 300	10	Hard and clear
20	TEGDM	13	LMA	7		80	Semi-soft, white opaque
21	TPETH	54	PHA	36	Mineral oil	10	Hard-powdery, white opaque
22	TPETH	15	PHA	15	Mineral oil	70	Semi-soft, white opaque
23	TMPTH	45	HEMA	45	Petroleum jelly	10	Semi-soft, white opaque
24	TMPTH	15	HEMA	5	Petroleum jelly	80	Semi-soft, white opaque

5  
10  
15  
20  
25  
30  
35  
40  
45  
50

Test No.	Cross-linking Monomer	Weight %	Mono Functional Monomer	Weight %	Material Entrapped	Weight %	Appearance in Test Tube
25	EGDM	45	LMA	45	Mineral spirits	10	Hard powdery, white opaque
26	EGDM	16.8	LMA	6.2	Mineral spirits	75	Semi-hard, white opaque
27	TEGDM	12.5	LMA	12.5	Lenolin	75	Semi-soft, yellow opaque
28	EGDM	60	SMA	30	Poly-Hexa-methyl dialloxane	10	Very hard, white opaque
29	EGDM	15	SMA	5	(Dow® Q2-1096)	80	Hard, powdery, white opaque
30	EGDM	60	LMA	30	Poly dimethyl (cyclic) siloxane	10	Hard, powdery, white opaque
31	EGDM	22.5	LMA	7.5	(Dow® J44 & J43)	70	Hard, powdery, white opaque
32	EGDM	45	DAA	45	Poly Dimethyl(Lin ear) Siloxane (Dow® 200)	10	Very hard, white opaque
33	EGDM	10	DAA	10		80	Semi-hard, white opaque

55 The following examples demonstrate formation of the lattice-entrapped materials of this invention.

EXAMPLE

1.20 grams of polyvinyl pyrrolidone having a K value of about 80 to 100 and available from Dan River, Inc., was dissolved in 1500 ml of water in a 2000 ml three necked resin flask equipped with a stirrer, thermometer and nitrogen purge. A solution of 335 grams of 2 ethylhexyl oxystearate (WICKENOL® 171), 132 grams ethylene glycol dimethacrylate, 33 grams 2-ethylhexyl methacrylate and 5 ml t-butyl peroctoate was bubbled with nitrogen for 5 minutes. The resultant monomer mix was slowly added to the stirred aqueous solution of polyvinyl pyrrolidone at 22°C under nitrogen. The temperature was raised to 80°C with constant agitation and held until polymerization started in approximately 15 minutes, and maintained at 80°C for an additional 2 hours to complete the reaction. Semi-soft, white opaque beads were collected by filtering off the supernatant liquid and dried to remove any excess water. The beads weighed 450 g for a yield of 90%, and were 0.25 to 0.5 mm in diameter. Other protective colloids such as starch, polyvinyl alcohol, carboxymethyl cellulose, methyl cellulose, or inorganic systems such as divalent alkali metal hydroxides, for example  $Mg(OH)_2$ , may be used in place of the polyvinyl pyrrolidone suspending medium. The composition is especially useful for incorporation of a pharmaceutical ingredient in combination with the ethylhexyl oxystearate for topical administration.

EXAMPLE 5

The procedure of Example 4 was repeated except that in each case 337.5 g arachidyl propionate (WAXENOL®801), or 337.5 g mineral oil, or 350 g cyclic polydimethyl siloxane (DOW®345), or 350 g petroleum distillate (150 to 160°C boiling point), or 325 g petroleum jelly, or 350 g isopropyl isostearate (WICKENOL® 131), or 375 g. Di (2 ethylhexyl) adipate (WICKENOL® 158), were substituted for 2-ethylhexyl oxystearate. In each case, semi-soft, white opaque beads were collected in good yield. These beads may be incorporated into topically applied pharmaceutical products and sunscreens where they demonstrate their desired effect by making the lattice-entrapped emollient-moisturizer available for application to the skin. The particle size of the resultant bead in each case was between 0.25 to 0.5 mm in diameter. The precise particle size varied somewhat due to the degree and rate of agitation during polymerization and the rates of the components to the water in which the polymerization system was suspended.

In combination with or in lieu of any one of the functional materials mentioned in this example may be used as a suitable pharmaceutical agent for topical use or a suncreening agent.

The following examples demonstrate compositions in which the lattice-entrapped functional materials of this invention have been incorporated.

EXAMPLE

Translucent Pressed Powder

5	<u>Translucent Pressed Powder</u>	
	Talc	77.64
10	Kaolin	14.00
	75% Arachidyl- propionate en- trapped bead of	
15	Example 5	5.00
	Magnesium carbonate	2.00
	Colorants	0.31
20	Methyl paraben	0.10
	Propyl paraben	0.10
25	Germall® 115	0.10
	Fragrance	<u>0.75</u>
		100.00

30

The components were combined in accordance with conventional formulation techniques. The lattice-entrapped emollients (Example 5 product) provided a pressed powder with desired emollient properties and application of the product to the body made the emollient available by rubbing. The pressed powder was remarkably resistant to breakage crumbling and glazing.

35

EXAMPLE 7

40 Milled Toilet Soap

	Toilet soap <sup>1</sup> base of tallow and coconut	89.00
45	2-ethylhexyl oxystearate entrapped bead of Example 4	10.00
	Fragrance	<u>1.00</u>
50		100.00

55 1. Duveen Soap Corporation, 154 Morgan Avenue, Brooklyn, New York  
The components were combined in accordance with conventional formulation techniques. The lattice-entrapped emollient (Example 4) provided the soap with the desired emollient properties. In addition, the physical attributes of the soap were enhanced, rendering it more resistant to cracking in use and less brittle. The soap had excellent lathering properties.

## EXAMPLE

Body Powder

5

10

15

Talc	84.5
Fragrance	0.5
2-ethylhexyl oxy- stearate entrapped bead of Example 4	10.0
Syloid #74	<u>5.0</u>
	100.00

20

The components were combined in accordance with conventional formulation techniques. The lattice-entrapped emollient (Example 4) provided the body powder with the desired emollient properties. In addition, the physical properties of the body powder were enhanced by providing increased adhesion to the body. The talc prior to entrapment may be combined with undecylenic acid to provide anti-fungal utility.

25

30

35

40

45

50

55

# EXAMPLE

## Antiperspirant Stick

5	<u>Phase A</u>	
	Stearyl Alcohol	25.0
10	Synthetic Beeswax Flakes <sup>a</sup> WAXENOL® 821	10.0
	Myristyl Myristate <sup>a</sup> WAXENOL® 810	17.5
15	Propylene Glycol Stearate	12.5
	<u>Phase B</u>	
20	Aluminum chlorhydrate <sup>a</sup> WICKENOL® CPS 325	25.0
	<u>Phase C</u>	
25	2-Ethylhexyl oxystearate en- trapped bead of Example 4	5.0
	Di-octyl adipate entrapped bead of Example 5	<u>5.00</u>
30		100.00

a. Wickhen Products, Inc. Huguenot, New York 12746

The antiperspirant stick formulations were prepared by heating the components of Phase A to 65-70°C. until melted, adding the component of Phase B without further heating and with constant and continuous agitation followed by slow addition of the components of Phase C with constant agitation until a uniform mixture is obtained. The mixture was then cooled somewhat and poured into molds at temperatures of from about 50 to 55°C. The antiperspirant stick had enhanced rigidity and strength and the desired emollient properties without tackiness.

In lieu of aluminum chlorhydrate there may be added a topically active pharmaceutical agent for the treatment of dermatological disorders, i.e. corticosteroids, fluorouracil, salicylic acid, clotrimazole, zinc glycinate, and the like, or a sunscreensing agent.

## EXAMPLE 10

Following the procedures of Example 1, test tube polymerization was completed utilizing different pheromones and varying types of monomer constituents and their ratios. The following abbreviations are used in Table II:

- LM n-Lauryl methacrylate
- EG Ethylene glycol dimethacrylate
- STM Stearyl methacrylate
- PHE Phenoxyethyl methacrylate
- CHM Cyclohexyl methacrylate

The Pheronome sample for Podisus Maculiventris prepared in a polypropylene test tube, diameter 4.5mm, was cut into plugs or cylinders, length 15mm and suspended in a polycarbonate tubing.

Air was blown around the sample a 1 liter/minute at 20°C and 10-15% of relative humidity.

The release was followed by weight loss of the sample. A constant rate period at  $1.67 \cdot 10^{-5} \text{g/hr.}$  for 10 days was achieved.

Similarly the following release of pheromones was tested.

5

10

15

20

25

30

35

40

45

50

55



TABLE II

PIEROMONE	CONCENTRATION IN POLYMER %	POLYMER COMPOSITION	AVERAGE RELEASE RATE g/HR.	CONSTANT RATE* PERIOD LENGTH
Grandlure*	50	IM-EG 0.6/0.4	1.5 x 15-4	50
Grandlure	60	IM-EG 0.6/0.4	1.5 x 10-4	55
Grandlure	80	IM-EG 0.6/0.4	1.8 x 10-4	70
Grandlure	50	IM-EG 0.8/0.2	2.10-4	60
Grandlure	50	STM-EG 0.8/0.2	2.5 x 10-4	65
Trimedlure	70	PHE-EG 0.8/0.2	2.5 x 10-4	70
Trimedlure	50	CHM-EG 0.8/0.2	1.10-4	50
Trimedlure	60	CHM-EG 0.8/0.2	1.10-3	60
Trimedlure	70	CHM-EG 0.8/0.2	1.10-4	70
Methyl Eugenol	50	IM-EG 0.4/0.6	6.10-4	60
Methyl Eugenol	50	PHE-EG 0.4/0.6	6.10-4	60
Methyl Eugenol	50	PHE-EG 0.8/0.2	8.10-4	65
Cuelure-Malathion	60	CHM-EG 0.4/0.6	1.2 x 10-4	60

\* Cis-2-isopropenyl-1-methyl-cyclobutane-ethanol (30% Racemic)

\* The length of the constant rate period was determined as inflection point where the falling rate period begins.

EXAMPLE 11

DIAZINON (0.0 Diethyl-0-(2-isopropyl-4-methyl) thiophosphate), a pesticide, was entrapped in a system LM 0.2/EGO.8 mol. ratio. The amount of Diazinon was varied from 50 to 80%. The polymerization was performed at 80°C under nitrogen as in Example 10 (Pheromones). In each instance, clear homogeneous articles were obtained.

Similar procedures were used for several pesticides listed in Table III.

TABLE III

COMPOUND	% ENTRAPPED	MONOMERS/MOL RATIO		PRODUCT
S,S Dipropyl-O-Ethyl Phosphodithionate (ETHOPROP)	50	LM 0.5	EG 0.5	Clear, Hard
N,N Dimethyl Dodecyl	50	LM 0.7	EG 0.3	Clear
	50	LM 0.6	TETRA 0.4	Opaque
N,N Diethyl m-Toluanide (DEET)	70	LM 0.8	EG 0.2	Clear, Elastic
N-Methyl N-(3Tolyl) Thiono Carbanate (TINACTIN)	50	BM 0.8	EG 0.2	Clear, Hard
	50	LM 0.8	EG 0.2	Opaque, Hard
3-Phenoxy-Benzyl-d-cl <sub>5</sub> Trans Chrysantemate (SUMITHIRIN)	50	LM 0.8	EG 0.2	Clear, Brittle
	50	LM 0.5	EG 0.2	Sl. Opaque, Hard
	50	PHE 0.8	EG 0.2	Opaque, Hard
	50	ClM 0.8	EG 0.2	Clear, Hard
	50	BM 0.8	EG 0.2	Sl. Opaque, Hard

TABLE III (CONT.)

COMPOUND	% ENTRAPPED	MONOMERS/MOL RATIO		PRODUCT
0,0-Diethyl-0-(3,5,6 Trichloro-2 Pyridyl) Phosphonothionate (CHLORPYRIFOS)	50	LM 0.8	EG 0.2	Sl. Opaque, Hard
	50	LM 0.6	EG 0.4	Clear, Brittle
	60	LM 0.6	EG 0.4	Clear, Brittle
2,2 Dimethyl-3-(3 Methyl-5 (4- Methyl Ethyl-Phenoxy) 3 Pentenyl) OXIRANE	50	LM 0.8	EG 0.2	Clear, Brittle
	50	DAA 0.8	EG 0.2	Clear, Hard
2,4,4'Trichloro-2'Hydroxy Diphenyl Oxide (IRGASAN DP 300)	50-70	LM 0.9	EG 0.1	Clear, Hard
2, 4 Dibromo Salicyl 4'Bromoanilide (TEMASEPT)	50	VP 0.9	EG 0.1	Clear, Hard
(5 Benzyl-3-Furyl) Methyl-2,2-Dimethyl-3 (2 Methyl Propenyl Cyclopropane Carboxylate (SPB 1382)	50	LM 0.7	EG 0.3	Clear, Brittle
O,O-Dimethyl-S-(N-Methyl Carbamoyl Methyl) Phosphorodithionate (DINETHOATE)	50	LM 0.5	EG 0.5	Opaque, Hard

TABLE III (CONT.)

COMPOUND	% ENTRAPPED	MONOMERS/MOL. RATIO		PRODUCT
0,0-Diethyl-S-[(Ethyl Thio) Methyl] Phosphoro Dithionate (PHORATE)	50	LM 0.5	EG 0.5	Clear, Hard
0,0 Dimethyl-S-(1.2 Dicarboethoxyethyl) Dithionate (MALATHION)	50-80	LM 0.2-0.8	EG 0.8-0.2	Clear, Hard
	50-80	PHE 0.4-0.8	EG 0.6-0.2	Clear, Hard
1,2 Dichlorovinyl Dimethyl Phosphate (DDVP)	80	LM 0.8	EG 0.2	Clear, Elastic
1-2-Allyl-4-Hydroxy-3-Methyl-2-Cyclopenten-1-One Ester of Trans Chrysanthemum Monocarboxylic Acid (d-TRANS-ALLETHRIN)	50-70	LM 0.8-0.5	EG 0.2-0.5	Clear, Soft Hard
Isopropyl (2E-4E)-11-Methoxy-3,7,11-Trinethyl-2,4 Dodecadienoate (METHOPRINE)	50-70	LM 0.8-0.5	EG 0.2-0.5	Clear, Soft Hard
Pyrethrins	50-80	LM 0.8-0.2	EG 0.2-0.8	Clear, Hard

5  
10  
15  
20  
25  
30  
35  
40  
45  
50  
55

COMPOUND	% ENTRAPPED	MONOMERS/MOL RATIO		PRODUCT
Bis (Tri-n-Butyl) Tin Oxide	50	IM 0.8-0.2	EG 0.2-0.8	Clear to Opaque Hard
1-(4-(1.1 Dimethyl Ethyl) henoxy) Cyclohexyl 2-Propynyl Sulfite (CNITE)	50	IM 0.8-0.2	EG 0.2-0.8	Clear, Elastic to Hard
2-(Trichloromethyl Thio) ntalimide [Folpet]	10-60	LM 0.8-0.2	EG 0.2-0.8	Opaque

EXAMPLE 12

5 62.5g of d-trans Allethrin, 15.51g of Lauryl Methacrylate 49.9g of Tetraethylene Glycol Dimethacrylate and 1.25g of Dibenzoyl Peroxide were suspended under stirring in 375ml of deionized water containing 0.3g of polyvinyl Pyrrolidone D-90. The suspension was heated gradually to 80°C. After formation of solid beads, the suspension was heated another 2 hours at 85°C. The beads were filtered and air dried. Similar  
10 procedures using different monomers their ratio and ratios monomers/pesticides was used in preparation of other pesticides in bead form.

EXAMPLE 13

15 P-methoxy benzaldehyde, a fragrance, was entrapped in a system LM 0.8/EG 0.2 mol. in concentrations 10-80% using the procedure as in Example 10 (Pheromones). Clear products were obtained.

The same procedure was applied to several other fragrance components listed in Table IV.

20 Similarly, total fragrance formulations of unknown composition were entrapped in concentrations 10-80%.

Suspension polymerization rendering bead form was performed the same way as described in pesticides and pheromones.

25

30

35

40

45

50

55

TABLE IV

COMPOUND	% ENTRAPPED	MONOMERS/MOL RATIO		PRODUCT
n-Methoxybenzaldehyde (AUBEPINE)	10-80	IM 0.2-0.8	EG 0.2-0.8	Clear, Solid
n-Cyano-Methoxyphenol Aubepine Nitrile	10-80	IM 0.2-0.8	EG 0.2-0.8	Clear, Solid
Eugenol	10-50	IM 0.2	TETRA 0.8	Clear, Solid
Isoeugenol	10-50	IM 0.2	TETRA 0.8	Clear, Elastic
Methoxy 4 Methyl Phenol-2	10-50	IM 0.2	TETRA 0.8	Clear, Solid
Fir Needle Oil Siberian	10-50	IM 0.2	TETRA 0.8	Clear Solid
Ethyl Safranate (Safran)	10-50	IM 0.2	TETRA 0.8	Clear, Solid
Thuja Oil	10-50	IM 0.2	TETRA 0.8	Clear, Solid
Vetiver Oil Bourbon	10-50	IM 0.2	TETRA 0.8	Clear, Elastic



TABLE IV (CONT.)

COMPOUND	% ENTRAPPED	MONOMERS/MOI, RATIO		PRODUCT
Methyl Anthranilate	10-50	LM 0.2	TETRA 0.8	Clear, Solid
Dimethyl Anthranilate	10-50	LM 0.2	TETRA 0.8	Clear, Solid
Indole	10-50	LM 0.2	TETRA 0.8	Clear, Solid
Geranyl Acetate	20-80	LM 0.2-0.8	EG 0.8-0.2	Clear, Solid
Benzyl Acetate	20-80	LM 0.2-0.8	EG 0.8-0.2	Clear, Solid
Anthracene 08	10-50	LM 0.2	TETRA 0.8	Clear
Dihydro Myrcenol	10-50	LM 0.2	TETRA 0.8	Opaque
Linallyl Acetate	10-60	LM 0.2	TETRA 0.8	Opaque
Phenyl Ethyl Alcohol	10-80	LM 0.2	TETRA 0.8	Clear
Methyl Cinnamate	10-70	LM 0.2	TETRA 0.8	Opaque
Terpineol	10-60	LM 0.2	TETRA 0.8	Opaque
Diethyl Phthalate	10-70	LM 0.2	TETRA 0.8	Clear
Benzyl Salicylate	10-60	LM 0.2	TETRA 0.8	Clear

TABLE IV (CONT.)

COMPOUND	% ENTRAPPED	MONOMERS/MOL RATIO	PRODUCT
Benzyl Benzoate	10-60	LM 0.2	EG 0.8
			Opaque Hard

#### EXAMPLE 14

5

Several chemicals used in different fields of applications such as emollients, esters, sunscreens, siloxanes, etc., were entrapped using the procedure described in Example 10 (Pheromones). Details of the entrapment are given in Table V.

10

15

20

25

30

35

40

45

50

55

TABLE V

COMPOUND	% ENTRAPPED	MONOMERS/MOL. RATIO		PRODUCT
Menthol	60	CHM 0.8-0.2	EG 0.2-0.8	Hard, Clear
	75	STEM 0.7	EG 0.3	Clear, Soft
Soybean Oil	50	STEM 0.6	EG 0.4	Clear, Soft
d-Limonene	50	LM 0.8	EG 0.2	Clear, Elastic
	50	LM 0.6	EG 0.2	Clear, Hard
	50	LM 0.5	EG 0.5	Clear, Hard
Methyl Nonyl Ketone	50	LM 0.8	EG 0.2	Clear, Brittle
	50	LM 0.5	EG 0.5	Opaque, Hard
Cinnamic Aldehyde	50	LM 0.8	EG 0.2	Clear, Soft
	50	LM 0.5	EG 0.5	Clear, Hard
Vitamin E	55-75	LM 0.3	EG 0.7	Opaque, Hard to Soft

TABLE V (CONT.)

COMPOUND	% ENTRAPPED	MONOMERS/MOL. RATIO		PRODUCT
Di (2-Ethylhexyl) Adipate	60-80	IM 0.3	EG 0.7	Opaque, Hard to Soft
Myristyl Lactate	80-85	IM 0.3	EG 0.7	Opaque, Soft
2-Ethylhexyl Palmitate	65	IM 0.3	EG 0.7	Opaque, Soft
Octyl Salicylate	20-60	IM 0.2	EG 0.8	Opaque, Soft
Dimethylamino Benzoic Acid Pentyl Ester (ESCALOL 506)	20-60	IM 0.2	EG 0.8	Clear, Solid
n-Dimethylamino Benzoic Acid 2-Ethylhexyl Ester	20-60	IM 0.2	EG 0.8	Clear, Solid
2-Hydroxy-4 Methoxy- Benzophenone (OXYREZONE)	20-60	IM 0.2	EG 0.8	Clear, Solid
Salicylic Acid	50	HM 0.6 IM 0.2	TETRA 0.2	Opaque, Hard
Methyl Salicylate	60	IBOMA 0.7	EG 0.3	Clear, Hard

TABLE V (CONT.)

COMPOUND	% ENTRAPPED	MONOMERS/MOL RATIO	PRODUCT
1,8,9 Anthralene Triol and Mineral Oil	60	IM 0.2	EG 0.4 Opaque, Hard
2,6,10,15,19,23 Hexamethyl Tetra Cosane (SQUALANE)	25-60	-DEC 50	EG 50 Clear, Soft
	25-60	CHM 50-75	EG 50-25 Clear, Hard to Soft
	25-60	STEM 50-80	EG 50-20 Opaque, Soft
Simethicon Straight Chain Poly- Siloxane	60	STEM 40	EG 60 Opaque, Soft
Dimethymino Oleate	50	STEM 0.8-0.5	EG 0.2-0.5 Clear, Soft
Decamethyl Cyclo Penta Siloxane	60-70	STEM 0.6-0.7	EG 0.4-0.3 Opaque, Hard to Soft
Dimethyl Laurylamine Oleate	35-50	STEM 0.5-0.6	EG 0.4-0.5 Opaque, Soft
Mineral Oil	45-60	STEM 0.6	EG 0.4 Opaque, Soft
Pentalyn H in Isopar G	50-70	STEM 0.5-0.7	EG 0.5-0.3 Opaque, Soft

55 50 45 40 35 30 25 20 15 10 5

TABLE V (CONT.)

COMPOUND	% ENTRAPPED	MONOMERS/MOL RATIO	PRODUCT
2-Ethylhexyl Oxystearate (WICKENOL 171)	70	STEM 0.8 EG 0.2	Clear, Soft
Isopropyl Isostearate (WICKENOL 131)	67	STEM 0.8 EG 0.2	Opaque, Soft
Octyl Dodecyl Myristate (WICKENOL 142)	60	STEM 0.8 EG 0.2	Clear, Soft
Isopropyl Myristate	70	LM 0.95-0.05 EG 0.05-0.95	Clear to Opaque Soft to Hard
Soybean Oil	50	STEM 0.6-0.8 EG 0.4-0.2	Clear, Elastic
Bisabolol Racemic	25	STEM 0.4 EG 0.6	Clear, Hard
	25	CM 0.8-0.4 EG 0.2-0.6	Clear, Hard
Tetrakis (2 Chloroethyl) Ethylene Diphosphate (Thermolin 101)		LM 0.2 EG 0.8	Hazy Soft
Bromochlorinated Paraffin		LM 0.8-0.2 EG 0.2-0.8	Clear, Soft to Hard

- Similarly, other chemicals and combinations were entrapped:  
Benzophenone and 2-ethylhexyl oxystearate (1:1 nt)  
Oleyl alcohol and glycerine esters  
5 Petroleum distillate and glycerine esters  
Petroleum distillate  
Jojoba Oil  
Citrus Oil

10

## Claims

A solid, lattice-entrapped non-cosmetic functional material composition comprising:  
from approximately 5% to approximately 95% by weight of a cross-linked hydrophobic comb-like polymer  
15 lattice;

from approximately 95% to about 5% by weight of a water insoluble liquid or solid functional material;  
said functional material being dispersed uniformly throughout and entrapped within said polymer lattice.

2. A lattice-entrapped functional material composition as claimed in claim 1, wherein said functional  
material and the monomers of said cross-linked copolymer are polymerized in situ.

20 3. A lattice-entrapped functional material composition as claimed in claim 1 or 2, wherein said cross-  
linked polymer matrix comprises:

a functional cross-linking monomer selected from the group consisting of di- or polyfunctional monomers  
having at least two polymerizable double bonds; and

25 a monofunctional monomer selected from the group consisting of polymerizable monomers having one  
double bond.

4. A lattice-entrapped functional material composition as claimed in any claim of claims 1 to 3, wherein  
said polyfunctional cross-linking monomer is a poly-unsaturated monomer selected from the group consist-  
ing of a mono- or di- or polyester of mono-, di-, or polyvalent alcohol, and alpha-beta unsaturated carboxylic  
acid, polyunsaturated polyvinyl ether of a polyvalent alcohol, mono- or polyunsaturated amides and  
30 cycloaliphatic esters of alpha-beta unsaturated carboxylic acids.

5. A lattice-entrapped functional material composition as claimed in claim 3 or 4, wherein said  
monofunctional monomer is selected from the group consisting of hydrophobic and hydrophylic monoun-  
saturated monomers.

35 6. A lattice-entrapped functional material composition as claimed in any of the preceding claims,  
wherein said functional material comprises a pesticidal agent, a pheromone, a pharmaceutical agent, an  
anti-microbial agent, a sunscreen or light stabilizer, a food flavorant, a pigment and/or a synthetic insect  
attractant.

7. A lattice-entrapped functional material composition as claimed in any of the preceding claims,  
wherein said polymer lattice is syneresis-free.

40 8. A lattice-entrapped functional material composition as claimed in any of the preceding claims,  
wherein said functional material comprises a herbicide and/or a fungicide.

9. A lattice-entrapped functional material composition as claimed in claim 6, wherein said pesticidal  
agent is a juvenile hormone analog.

10. A lattice-entrapped functional material composition as claimed in claim 6, wherein said food  
45 flavorant is a sweetener.

11. A lattice-entrapped functional material composition as claimed in any of the preceding claims,  
wherein said composition comprises free-flowing powders, free-flowing beads and/or a plug.

12. A lattice-entrapped functional material composition as claimed in claim 11, wherein said plug is in  
cylinder form.

50 13. A lattice-entrapped functional material composition as claimed in claim 5, wherein said monomers  
are alkyl methacrylates and acrylates having straight or branch chain alkyl groups with 1 to 30 carbon  
atoms and are especially selected from the group consisting of lauryl methacrylate, 2-ethylhexyl  
methacrylate, isodecylmethacrylamide, diacetone acrylamide and methoxy ethyl methacrylate.

55






FIG. 1a




FIG. 1b



FIG. 1c



FIG. 1d



FIG.2a



FIG.2b




FIG.2c



FIG.2d




FIG.3a



FIG.3b



FIG.3c




FIG.3d



FIG.4a




FIG.4b




FIG.4c

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11)

Publication number:

**0 252 463**  
**A3**

(12)

# EUROPEAN PATENT APPLICATION

(21) Application number: 87109662.4

(51) Int. Cl.<sup>4</sup>: C08F 220/10 , C08F 2/44 ,  
A01N 25/10 , A61K 9/22 ,  
A61K 47/00 , A23L 1/22 ,  
A23L 1/236 , A23L 1/275

(22) Date of filing: 04.07.87

(30) Priority: 07.07.86 US 882609  
20.05.87 US 53609

(43) Date of publication of application:  
13.01.88 Bulletin 88/02

(84) Designated Contracting States:  
BE CH DE FR GB IT LI NL

(88) Date of deferred publication of the search report:  
12.07.89 Bulletin 89/28

(71) Applicant: DOW CORNING CORPORATION  
Midland Michigan 48640(US)

(72) Inventor: Abrutyn, Eric S.  
9 Westminister Drive  
Middletown NY 10940(US)  
Inventor: Chromecek, Richard C.  
RFD 1  
Litchfield Conn. 06759(US)  
Inventor: Scarfo, Louis J.  
18 Lyons Place  
New Britain Conn. 06052(US)

(74) Representative: Patentanwälte RUFF, BEIER  
und SCHÖNDORF  
Neckarstrasse 50  
D-7000 Stuttgart 1(DE)

(54) Lattice-entrapped composition.

(57) This invention relates to solid compositions wherein a non-cosmetic functional material is entrapped in the lattice of the cross-linked polymer during in situ polymerization of the monomers forming the polymer lattice. The invention provides for conversion of solid and/or liquid products into solid, free-flowing forms by entrapment of the functional materials in a hydrophobic polymer lattice.

EP 0 252 463 A3



DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
X	EP-A-0 201 214 (NIPPON PAINT CO.) * Claims 1-4,6-7; examples 1,5; page 16, lines 9-19; page 5, line 11 - page 7, line 1 * ---	1-8,13	C 08 F 220/10 C 08 F 2/44 A 01 N 25/10 A 61 K 9/22 A 61 K 47/00
X	US-A-3 590 018 (S.E. GEBURA et al.) * Claim 1; page 1, lines 54-59 * ---	1-7,13	A 23 L 1/22 A 23 L 1/236
A	GB-A-1 469 072 (NATIONAL FOOD RESEARCH INSTITUTE) * Claims 1,4,6,12 * ---	1,5-7	A 23 L 1/275
A	EP-A-0 067 595 (WARNER-LAMBERT CO.) * Claims 1,11 * -----	1,5-6,10	
			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			C 08 F A 01 N A 23 L
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 19-04-1989	Examiner TAISNE S.M.T.
<b>CATEGORY OF CITED DOCUMENTS</b> X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document			

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**